



ASTM D6817 Geofoam / Expanded Polystyrene Physical Property Requirements

Type		EPS12	EPS15	EPS19	EPS22	EPS29	EPS39	EPS46
Property	ASTM Test	Values						
Density lb/ft ³	D1622	.70 min.	.90 min.	1.15 min.	1.35 min.	1.80 min.	2.40 min.	2.85 min.
Compressive Resistance Min. psi at 1% Min. psi at 5 % Min. psi at 10%	D1621 D1621 D1621	2.2 5.1 5.8	3.6 8.0 10.2	5.8 13.1 16.0	7.3 16.7 19.6	10.9 24.7 29.0	15.0 35.0 40.0	18.6 43.5 50.0
Flexural Strength Min. psi	C203	10	25	30	35	50	60	75
Oxygen Index Min. Volume %	D2863	24	24	24	24	24	24	24
Water Absorption (by total immersion) Max. % by volume	C272	4.0	4.0	3.0	3.0	2.0	2.0	2.0

96 Fourth Avenue
Haskell, NJ 07420
USA

Toll Free: 800.229.7161
Office: 973.835.7161
Fax: 973.835.2438

Email: info@polymoldingllc.com
Web: www.polymoldingllc.com

